

Technical Data Sheet

Natural Red Iron Oxide FPA RED[®]-NH4

This Technical Data Sheet includes the values and data which are valid and trustable based on our current production process, but not legally binding. We hereby disclaim any liability arising from any damage, errors and omissions or consequential damage.

This Technical Data Sheet supersedes all previous versions. (December 2022)

Chemical Analysis		Physical Properties / Particle Size	
CaO (%)	5.06	Mean grain size D50 (µ)	5.84
K2O (%)	0.63	Top – cut D97 (μ)	23.2
MgO (%)	2.32	Specific Gravity (g/ cm ³)	4.26
Fe2O3 (%)	62.66	Apperance	Red
AI2O3 (%)	1.95		
SiO2 (%)	12.23		
TiO2 (%)	0.146		
Na2O (%)	0.50	Applications;	Standard Packaging;
SO3 (%)	4.50		25 Kg PP bag
P2O5 (%)	0.070		Bulk in Jumbo bag 25 Kg bags in Jumbo bag 25 Kg bags on pallet
Loss of Ignition (%)	8.03		

Head Office; 3rd Floor., No. 20, Baharan Alley, Shirazi Str., Tehran, Iran Tel: +98 (21) 88032858

Fax.: +98 (21) 88032688

Plant;

Industrial Zone, Dodehak Village, Delijan, Markazi Province, Iran Tel: +98 (86) 44260388 Fax.: +98 (86) 44260401



web: www.farayandpowder.com E-mail: export@farayandpowder.com